



Advanced Paver Product Data Sheet

Testing

Property	Value	Test Method
Compressive Strength	> 9,500 psi avg. with no individual unit less than 8,500psi	ASTM C 140
Water Absorption	< 4%	ASTM C 140
Flexural Strength	> 800 psi. avg.	ASTM C 293
Freeze/Thaw	< 0.1 % loss of dry weight (50 Cycles)	ASTM C 1262
Center Load	2000 lbs.	WTCL 99

Sizes and Weights

Standard available sizes square pavers (nominal): 12", 18", 24", 30", 36", 40" and 42" sq.

Standard available sizes rectangular pavers (nominal):

Widths: 3", 4", 6", 9", 12", 15", 16", 18", 24", 30", 36" and 42".

Lengths: 12", 16", 18", 24", 30", 36", 42", and 48".

Thickness: 2", 2 3/4", 3", and 4"

Weight: 24 to 48 lbs. /sq. ft.

Dimensional tolerance: +/- 1/16" (Length, width, height, convex, concave).

Custom sizes and thickness, available upon request.

Tectura Designs
E-mail: wtile@wausatile.com
Phone: 800-388-8728
Fax: 715-359-7456
Tecturadesigns.com